



PATENT APPLICATION

IN THE UNITED STATES PATENTS AND TRADEMARK OFFICE

#8
KCO
1-3003

In re Application of

Tsuyoshi INOUE, et al.

Appln. No. : 09/874,314

Confirmation No.: 6107

Group Art Unit: 1755

Filed: June 06, 2001

Examiner: 1771

For: SHEET FOR PROTECTING PAINT FILM

DECLARATION UNDER 37 C.F.R. 1.55(b)
(Pursuant to 37 C.F.R. 1.68)

Honorable Commissioner of
Patents and Trademarks
Washington, D.C. 20231

Sir:


I, Hiroshi Okamoto, do depose, declare and state:

THAT I am a citizen of Japan located at Ark Mori Bldg. 28F, 12-32, Akasaka 1-chome, Minato-ku, Tokyo 107, Japan.

THAT I understand the Japanese and English languages and that the attached English document is believed to be full, true and faithful translation made by me of Japanese Patent Application No. 2000-173048, the claim to the priority date of which application was made in the letter of transmittal submitted with the application as filed, with receipt of the certified copy of said Japanese application being acknowledged by the U.S. Patent Office in the Office Action dated August 13, 2002, Paper Number 5.

I declare further that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under §1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

Date: December 19, 2002

A handwritten signature in black ink, appearing to read 'H. Okamoto', is written over a horizontal line.

Hiroshi Okamoto

[Name of the Document]	Patent Application
[Reference No.]	00NP285
[Addressed To]	Commissioner, Patent Office Esq.
[International Patent Classification]	C09J 7/02
[Inventor]	
[Address or Residence]	c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi, Osaka
[Name]	Tsuyoshi Inoue
[Inventor]	
[Address or Residence]	c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi, Osaka
[Name]	Kenji Sano
[Inventor]	
[Address or Residence]	c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi, Osaka
[Name]	Yoshiki Kobayashi
[Inventor]	
[Address or Residence]	c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi, Osaka
[Name]	Kenichi Shibata
[Inventor]	
[Address or Residence]	c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi, Osaka
[Name]	Keiji Hayashi
[Inventor]	
[Address or Residence]	c/o Nitto Denko Corporation, 1-2, Shimohozumi 1-chome, Ibaraki-shi, Osaka
[Name]	Mitsuru Horada
[Inventor]	
[Address or Residence]	c/o Kansai Paint Co., Ltd., 17-1, Higashi-Yahata 4-chome, Hiratsuka-shi, Kanagawa
[Name]	Komaharu Matsui

[Inventor]

[Address or Residence] c/o Kansai Paint Co., Ltd.,
17-1, Higashi-Yahata 4-chome, Hiratsuka-shi, Kanagawa

[Name] Yu Akaki

[Inventor]

[Address or Residence] c/o Kansai Paint Co., Ltd.,
33-1, Kanzaki-cho, Amagasaki-shi, Hyogo

[Name] Takeshi Eda

[Inventor]

[Address or Residence] c/o Kansai Paint Co., Ltd.,
33-1, Kanzaki-cho, Amagasaki-shi, Hyogo

[Name] Hiroshi Ueda

[Applicant for Patent]

[Identification No.] 000003964

[Name or Appellation] NITTO DENKO CORPORATION

[Representative] Hideki Yamamoto

[Applicant for Patent]

[Identification No.] 000001409

[Name or Appellation] KANSAI PAINT CO., LTD.

[Representative] Tamotsu Shirowa

[Agent]

[Identification No.] 100088007

[Patent Attorney]

[Name or Appellation] Tsutomu Fujimoto

[Indication of Fee]

[Deposit Account Book No.] 052386

[Amount] ¥21,000

[List of the Filed Documents]

[Name of the Document] Specification 1

[Name of the Document] Abstract 1

[General Power of Attorney No.] 9006504

[General Power of Attorney No.] 9710228

[Request for Proof] Yes

[Designation of Document] Specification

[Title of the Invention]

Sheet for protecting paint film

[Claims]

[Claim 1] A sheet for protecting a paint film, characterized in that a rubber-based pressure-sensitive adhesive layer comprising a blend of at least a copolymer of an aromatic compound and a terpene compound or aliphatic hydrocarbon compound, with a rubbery polymer is formed on a substrate.

[Claim 2] The sheet for protecting a paint film of claim 1, wherein the amount of the copolymer blended is 0.2-5 parts by weight per 100 parts by weight of the rubbery polymer.

[Detailed Description of the Invention]

[0001]

[Technical Field of the Invention]

The present invention relates to a sheet for protecting a paint film which, even when applied to a paint film on which fouling substances are apt to remain after protective sheet removal, can be satisfactorily adhered efficiently to the paint film and can be easily peeled therefrom after long-term adhesion without fouling the paint film, and which is suitable for the surface protection of automotive bodies and parts, coated steel sheets, etc.

[0002]

[Prior Art]

A protective coating formed by applying a wax type coating material in a thickness of from 5 to 40 μm has conventionally been known as a means for preventing the paint films of coated automobiles, coated automotive parts, and the like from being damaged or impaired in gloss, color, etc., by suspended or colliding matters such as dust particles, rain, and stone debris when such coated products are loaded on trucks or ships

and transported to remote areas such as overseas countries. However, this means has had the following and other problems. It is difficult to form a wax coating having an even thickness, so that even protection is difficult to obtain. Wax coatings are apt to soil and have poor resistance to acid rain. Components of the wax infiltrate into the paint film of the coated product to cause discoloration, etc. In addition, the formation and removal of wax coatings necessitate much labor and are apt to arouse environmental problems concerning use of a solvent, waste liquid treatment, etc.

[0003]

On the other hand, various surface-protective sheets are known which comprise a substrate and a pressure-sensitive adhesive layer formed thereon. Proposed for use in the protection of paint films is a protective sheet having a radiation-curable pressure-sensitive adhesive layer having a lowered glass transition point or a rubber-based pressure-sensitive adhesive layer comprising polyisobutylene or the like (see JP-A-2-199184 and JP-A-6-73352). This technique of paint film protection with a sheet is capable of eliminating the problems associated with the technique of paint film protection with a wax. However, the conventional protective sheet has had a problem that the sheet, when applied to paint films of some kinds, is apt to leave fouling substances on the paint films after peeling therefrom.

[0004]

[Technical Problems of the Invention]

The present inventors made intensive investigations in order to overcome the above-described problem by a sheet for protecting a paint film. As a result, they have found that the problem of fouling is attributable to that component mixing occurs at the interface between the paint film and the pressure-sensitive adhesive layer and, as a result, additives contained in the pressure-sensitive adhesive layer remain on the paint film surface after the protective sheet is peeled off.

[0005]

In view of the above, an object of the invention is to provide a sheet for paint film protection which can be efficiently applied and satisfactorily adhered to a paint film and retain the satisfactorily adherent state over long and which, after accomplishment of the protection, can be easily peeled off and is less apt to foul the paint film even when the paint film is of the type susceptible to fouling upon protective sheet removal, thereby necessitating no cleaning treatment.

[0006]

[Means for Solving the Problems]

The invention provides a sheet for protecting a paint film, characterized in that a rubber-based pressure-sensitive adhesive layer comprising a blend of at least a copolymer of an aromatic compound and a terpene compound or aliphatic hydrocarbon compound, with a rubbery polymer is formed on a substrate.

[0007]

[Advantage of the Invention]

According to the invention, a sheet for protecting a paint film can be obtained which can be efficiently applied and satisfactorily adhered to a paint film and retain the satisfactorily adherent state over a long period of time. The adherent sheet is less apt to pose the problem that it peels off by itself. Even when the paint film is of the type in which fouling substances are apt to remain after protective sheet removal, the sheet can be easily peeled therefrom after accomplishment of the protection and is less apt to leave fouling substances on the paint film due to the incorporation of the copolymer. No cleaning treatment is hence necessary. Although details of this effect are unclear, it is thought that the copolymer functions as a compatibilizing agent for the rubbery polymer and fouling substances to enable the fouling substances to remain in the pressure-sensitive adhesive layer without being transferred to the paint film surface.

[0008]

[Mode for Carrying Out the Invention]

The sheet for protecting a paint film according to the invention comprises a substrate having formed thereon a rubber-based pressure-sensitive adhesive layer comprising a blend of at least a copolymer of an aromatic compound and a terpene compound or aliphatic hydrocarbon compound, with a rubbery polymer. The rubbery polymer serving as the base polymer of the rubber-based pressure-sensitive adhesive layer is not particularly limited. One or more appropriate rubbery polymers can be used as the base polymer.

[0009]

Examples of the rubbery polymer include diene polymers such as polyisoprene and polybutadiene and hydrogenated polymers obtained therefrom; olefin polymers such as ethylene/propylene rubbers, ethylene/ α -olefin copolymers, ethylene/propylene/ α -olefin copolymers, and propylene/ α -olefin copolymers; butyl rubber and polyisobutylene; styrene/diene hydrocarbon random copolymers such as styrene/butadiene rubbers and hydrogenated copolymers obtained therefrom; A/B/A type styrene block polymers such as styrene/butadiene/styrene (SBS), styrene/isoprene/styrene (SIS), styrene/ethylene-butylene copolymer/styrene (SEBS), and styrene/ethylene-propylene copolymer/styrene (SEPS); A/B type styrene block polymers such as styrene/butadiene (SB), styrene/isoprene (SI), styrene/ethylene-butylene copolymer (SEB), and styrene/ethylene-propylene copolymer (SEP); A/B/C type crystalline styrene/olefin block polymers such as styrene/ethylene-butylene copolymer/olefin crystal (SEBC) and hydrogenated polymers obtained therefrom; C/B/C type crystalline olefin block polymers such as olefin crystal/ethylene-butylene copolymer/olefin crystal (CEBC) and hydrogenated polymers obtained therefrom; and styrene/olefin crystal block copolymers and hydrogenated polymers obtained therefrom.

[0010]

Examples of the copolymer of an aromatic compound with a terpene

compound or an aliphatic hydrocarbon compound, which is incorporated in the rubbery polymer, include copolymers having an aromatic moiety consisting of polystyrene or a phenolic, xylene, or another aromatic resin and a terpene or aliphatic hydrocarbon moiety consisting of a terpene resin, such as an (α,β)-pinene polymer or diterpene polymer, an aliphatic (including alicyclic) petroleum resin, a hydrogenated resin obtained therefrom, or the like. Specific examples thereof include styrene/hydrogenated terpene copolymer resins, phenol/terpene copolymer resins, phenol/hydrogenated terpene copolymer resins, aliphatic/aromatic copolymer petroleum resins, and partially hydrogenated resins obtained by hydrogenating the aliphatic moiety of the petroleum resins. The hydrogenated terpene resin is a resin obtained by partially or completely hydrogenating the terpene resin.

[0011]

Those copolymers can be used alone or in combination of two or more thereof. Styrene/hydrogenated terpene copolymer resins are preferred from the standpoints of long-term stability of pressure-sensitive adhesive properties, hue, adhesion to paint films, etc. The amount of the copolymer to be incorporated is generally 0.2-5 parts by weight, preferably 0.3-4 parts by weight, more preferably 0.5-3 parts by weight, per 100 parts by weight of the rubbery polymer from the standpoints of preventing the copolymer from serving as a substance which itself is causative of paint film fouling, and of preventing any substance from remaining on and fouling paint films. Even when incorporated in such a relatively small amount, the copolymer advantageously produces the effect of preventing substances which have bled from a paint film from causing paint film fouling after protective-sheet removal.

[0012]

Appropriate additives can be incorporated in forming the pressure-sensitive adhesive layer for the purpose of regulating pressure-sensitive adhesive properties, etc. Examples of such additives include softeners, silicone polymers, acrylic polymers,

tackifiers other than the copolymer described above, antioxidants, light stabilizers such as hindered amines, ultraviolet absorbers, fillers such as calcium oxide, magnesium oxide, silica, zinc oxide, and titanium oxide, and pigments. Even when the incorporation of such an additive may result in fouling due to interaction with a substance which has bled from a paint film, this fouling can be prevented by the incorporation of the copolymer described above.

[0013]

The incorporation of a softener is usually effective in improving adhesive strength. Examples of the softener include low molecular polymers such as polyisobutylene, ethylene/propylene rubbers, polyisoprene, and polybutadiene. One or more appropriate softeners can be used. Preferred softeners are low molecular polymers in which the unsaturated bonds have been hydrogenated, such as hydrogenated polyisoprene, hydrogenated polybutadiene, hydrogenated polybutadiene(mono or di)ol, hydrogenated liquid polyisoprene(mono or di)ol, and hydrogenated polybutadiene or polypropylene modified with a carboxylic acid.

[0014]

From the standpoint of moderately enhancing the strength of adhesion to paint films and other standpoints, it is preferred to use a softener having a number average molecular weight of 1,000-200,000, preferably 1,100-150,000, more preferably, 1,200-100,000. Although the amount of the softener to be incorporated can be suitably determined according to the desired adhesive strength, etc., it is generally 150 parts by weight or smaller, preferably 100 parts by weight or smaller, more preferably 60 parts by weight or smaller, per 100 parts by weight of the rubbery polymer.

[0015]

The incorporation of a silicone polymer is usually effective in improving peelability. One or more appropriate silicone polymers having a backbone made up of siloxane bonds and having any of a wide range of molecular weights can be used.

Examples thereof include dimethylpolysiloxane, methylphenylpolysiloxane, methylhydrogenpolysiloxane, and such polysiloxanes modified with epoxy, alkyl, amino, carboxyl, alcohol, fluorine, alkyl-aralkyl polyether, epoxy polyether, polyether, or the like. From the standpoints of attaining a satisfactory adherent state, stably maintaining peelability, etc., the amount of the silicone polymer to be incorporated is generally 5 parts by weight or smaller, preferably 3 parts by weight or smaller, more preferably from 0.005 to 2 parts by weight, per 100 parts by weight of the rubbery polymer.

[0016]

On the other hand, an acrylic polymer may be incorporated for the purposes of improving wetting ability to thereby enhance adhesion to paint films and inhibiting the adhesive strength from increasing with time in a high temperature atmosphere. It is preferred from these standpoints to use an acrylic polymer having a weight average molecular weight of 1,000-500,000. An acrylic polymer having a molecular weight in that range, which is liquid at ordinary temperature, is thought to function in the following manner. The acrylic polymer is present in a higher concentration in a surface layer of the pressure-sensitive adhesive layer because of its compatibility with the rubbery polymer to thereby satisfactorily wet paint films. Thus, the acrylic polymer enables the pressure-sensitive adhesive layer to satisfactorily adhere to paint films on which fouling substances are apt to remain after protective-sheet removal and to poorly bondable paint films and other paint films. Furthermore, the acrylic polymer is stable to heat and enables the protective sheet to be satisfactorily peeled off.

[0017]

If the acrylic polymer has a weight-average molecular weight lower than 1,000, there are cases where the effect of improving adhesive strength may be insufficient due to the too low molecular weight. If the molecular weight thereof exceeds 500,000, there are cases where the pressure-sensitive adhesive layer has poor

long-term stability or shows poor peelability after long-term adhesion. From the standpoints of improved adhesive strength, long-term stability, stable peelability, etc., it is preferred to use an acrylic polymer having a weight average molecular weight of 3,000-300,000, preferably 5,000-100,000, more preferably 10,000-50,000. From the standpoints of the ability to wet paint films, etc., it is preferred to use an acrylic polymer having a glass transition temperature of 25°C or lower, preferably 0°C or lower, more preferably -10°C or lower.

[0018]

Acrylic polymers can be used alone or in combination of two or more thereof. The acrylic polymers are not particularly limited in the monomers therefor, etc. Examples thereof include a polymer produced by polymerizing one or more (meth)acrylates having an alkyl group having 1 to 18 carbon atoms if desired with one or more copolymerizable monomers known for acrylic pressure-sensitive adhesives, such as (meth)acrylamide, by an appropriate method, e.g., solution polymerization. Examples of such acrylic polymers include commercial products available under the trade names of Polyflow No. 55 and Polyflow No. 50E (manufactured by Kyoeisha Chemical Co., Ltd.), Disparon LC-951, Disparon LC-955, and Disparon LC-1985 (manufactured by Kusumoto Chemicals Ltd.), and Modaflow (manufactured by Monsanto Co.).

[0019]

The amount of the acrylic polymer to be incorporated is preferably 0.05-40 parts by weight per 100 parts by weight of the rubbery polymer. If the amount thereof is smaller than 0.05 parts by weight, there are cases where the effect of improving adhesive strength is insufficient due to the too small incorporation amount. If the amount thereof exceeds 40 parts by weight, there are cases where the acrylic polymer is present in a higher concentration in a surface layer of the pressure-sensitive adhesive layer to considerably reduce the adhesive strength and this is apt to arouse troubles.

For example, when this protective sheet is applied to, e.g., the paint film of a motor vehicle and the vehicle is driven, the protective sheet peels off by itself. From the standpoints of attaining a satisfactory adherent state, etc., the amount of the acrylic polymer to be incorporated is preferably 30 parts by weight or smaller, more preferably 20 parts by weight or smaller, most preferably 0.1-10 parts by weight, per 100 parts by weight of the rubbery polymer.

[0020]

On the other hand, the incorporation of a tackifier also is usually effective in improving adhesive strength. One or more conventional appropriate tackifiers for use in pressure-sensitive adhesives may be used. Examples thereof include petroleum resins such as aliphatic, aromatic, and alicyclic petroleum resins, coumarone-indene resins, terpene homopolymer resins, (polymerized) rosin resins, (alkyl)phenolic resins, xylene resins, and resins obtained by hydrogenating these resins. The amount of the tackifier to be incorporated is preferably 100 parts by weight or smaller, more preferably 80 parts by weight or smaller, most preferably 60 parts by weight or smaller, per 100 parts by weight of the rubbery polymer from the standpoint of avoiding the problem of adhesive transfer and improving adhesive strength by inhibiting the cohesive force from decreasing. The copolymer described above is also effective as a tackifier.

[0021]

As the substrate on which a pressure-sensitive adhesive layer is to be formed, a suitable substance can be used according to, e.g., the intended use of the sheet for protecting a paint film. Examples of the substrate include a film, a porous film, a porous sheet such as a fibrous sheet or non-woven fabric, a foam, and a composite sheet obtained by laminating two or more thereof. In general, the substrate is constituted of a single polyolefin such as polyethylene or polypropylene, a mixture of two or more of such polyolefins, or a thermoplastic resin such as a polyester or polyamide. Of these substrate materials, polyolefins are especially preferred from the standpoint of

suitability for incineration after peeling. The porous sheet has an advantage that the protective sheet employing this substrate can have improved peelability because the pressure-sensitive adhesive layer formed on the porous substrate can have a surface reflecting the surface roughness of the substrate. Another advantage of the porous sheet is that because of its air permeability and moisture permeability, the protective sheet employing this substrate has the property of allowing infiltrated rain water to readily volatilize. Namely, the paint film from which this protective sheet has been peeled is less apt to bear traces of the protective sheet. The thickness of the substrate consisting of a film is generally 5-300 μm , preferably 20-100 μm . However, the thickness thereof should not be construed as being limited to that range.

[0022]

Appropriate additives such as those mentioned above may be incorporated into the substrate for the purposes of deterioration prevention, etc. Examples of the additives include antioxidants, ultraviolet absorbers, light stabilizers such as hindered amines, antistatic agents, and inorganic fillers. The substrate may be one having ultraviolet-shielding properties. Use of an ultraviolet-shielding substrate is desirable in that it prevents the deterioration of itself and of the pressure-sensitive adhesive layer outdoors and thereby enables the protective sheet to stably retain satisfactory peelability free from substrate breakage and adhesive transfer over long. An especially preferred ultraviolet-shielding substrate is one in which the transmittance of ultraviolet having wavelengths of 190-370 nm is 5% or lower, preferably 3% or lower, more preferably 1% or lower, most preferably 0.5% or lower.

[0023]

An ultraviolet-shielding substrate can be formed by an appropriate technique by, e.g., a method in which ultraviolet-shielding particles are dispersedly incorporated therein. Specific examples thereof include: a method in which a polymer containing ultraviolet-shielding particles is formed into a film or fibers by an

appropriate technique to form a film or laminated layer; a method in which these fibers are used to form a porous sheet; a method in which a coating fluid containing ultraviolet-shielding particles is deposited on a surface of a substrate-forming film, fibers, or laminated layer to form a coating film; and a method comprising forming a film of an appropriate metal, e.g., stainless steel, on a substrate by vapor deposition.

[0024]

Appropriate particles which reflect or absorb ultraviolet can be used as the ultraviolet-shielding particles. Examples thereof include titanium white, red iron oxide, zinc white, alumina, tin oxide, and carbon black. The coating fluid can, for example, be a dispersion obtained by mixing a binder ingredient comprising an appropriate resin such as an acrylic, urethane, or polyester resin with ultraviolet-shielding particles in a medium comprising an appropriate organic solvent, e.g., toluene, water, or the like.

[0025]

For forming the sheet for protecting a paint film, a known technique for forming an adhesive sheet can be used. Examples thereof include: a method in which either a solution of a material for forming a pressure-sensitive adhesive layer in a solvent or a melt of the material is applied to a substrate; a method in which a pressure-sensitive adhesive layer is formed on a separator by that method and is then transferred to a substrate; a method in which a material for forming a pressure-sensitive adhesive layer is applied to a substrate by extrusion coating; a method in which a material for forming a substrate and a material for forming a pressure-sensitive adhesive layer are coextruded in two or more layers; a method in which a pressure-sensitive adhesive layer alone is laminated to a substrate; a method in which a pressure-sensitive adhesive layer and another layer are laminated to a substrate; and a method in which a pressure-sensitive adhesive layer and one or more substrate-forming materials such as a film and laminated layer are formed by laminating.

[0026]

Although the pressure-sensitive adhesive layer may have been formed over the whole one-side surface of the substrate by any of the methods described above or another method, it may be one formed so as to be air-permeable. Examples of such a pressure-sensitive adhesive layer include a layer formed by a method in which a material for forming a pressure-sensitive adhesive layer is formed into fibers by an appropriate technique such as, e.g., melt blowing or curtain spraying and the fibers are deposited in a layered arrangement, especially in the form of non-woven fabric or the like, and further include a patterned pressure-sensitive adhesive layer formed by partly coating a substrate with a pressure-sensitive adhesive in the form of dots, stripe, etc.

[0027]

A pressure-sensitive adhesive layer having an embossing or having a finely roughened surface structure reflecting the surface roughness of a substrate may be formed. This pressure-sensitive adhesive layer has an advantage that air bubble trapping and other troubles are less apt to occur when the protective sheet is applied. Although the thickness of the pressure-sensitive adhesive layer to be formed may be suitably determined according to the desired adhesive strength, etc., it is generally 100 μm or smaller, preferably 1-50 μm , more preferably 3-20 μm . If desired, the pressure-sensitive adhesive layer may be protected by provisionally covering it with a separator or the like until use.

[0028]

That side of the substrate on which a pressure-sensitive adhesive layer is to be formed may be subjected according to need to a surface treatment for improving adhesion of the pressure-sensitive adhesive layer, etc. Examples of the treatment include corona treatment, flame treatment, plasma treatment, sputtering/etching treatment, and coating with a primer or the like. On the other hand, a coating layer comprising an appropriate release agent such as a silicone, long chain alkyl resin, or fluoro-resin may be formed on that side of the substrate on which a pressure-sensitive

adhesive layer is not formed, for the purpose of, e.g., obtaining a roll which can be easily unwound. The surface of the pressure-sensitive adhesive layer also may be subjected according to need to a suitable surface treatment such as those mentioned above for the purpose of regulating the pressure-sensitive adhesive properties, etc.

[0029]

The sheet for protecting a paint film according to the invention can be advantageously applied to coated adherends such as automotive bodies, automotive parts including bumpers, metal sheets including steel sheets, and formed metal sheets for the purpose of surface protection against colliding minute substances, chemicals, etc. or for other purposes. Such coated adherends are, for example, products or parts coated with a paint film based on a polyester-melamine, alkyd-melamine, acrylic-melamine, or acrylic-urethane resin, an acrylic/polyacid hardener system, etc. However, the paint film is not particularly limited.

[0030]

[Examples]

EXAMPLE 1

In 700 parts of toluene were dissolved 75 parts (parts by weight; the same applies hereinafter) of polyisobutylene having a weight average molecular weight, measured by gel permeation chromatography and calculated for standard polystyrene (the same applies hereinafter), of 870,000, 25 parts of polyisobutylene having a weight average molecular weight of 80,000, and 1 part of a styrene/hydrogenated terpene copolymer resin (Clearon K100, manufactured by Yasuhara Chemical Co., Ltd.). This solution was applied to one side of a 40 μm -thick film of a polypropylene/polyethylene blend. The coating was heated at 80°C for 3 minutes to form a rubber-based pressure-sensitive adhesive layer having a thickness of 10 μm . Thus, a sheet for protecting a paint film was obtained.

[0031]

EXAMPLE 2

A sheet for protecting a paint film was obtained in the same manner as in Example 1, except that the amount of the styrene/hydrogenated terpene copolymer resin was changed to 0.5 parts.

[0032]

EXAMPLE 3

A sheet for protecting a paint film was obtained in the same manner as in Example 1, except that the amount of the styrene/hydrogenated terpene copolymer resin was changed to 3 parts.

[0033]

EXAMPLE 4

A sheet for protecting a paint film was obtained in the same manner as in Example 1, except that the amount of the styrene/hydrogenated terpene copolymer resin was changed to 0.2 parts.

[0034]

EXAMPLE 5

A sheet for protecting a paint film was obtained in the same manner as in Example 1, except that a hydrogenated polymer (Arkon M-100, manufactured by Arakawa Chemical Industries, Ltd.) obtained by hydrogenating the non-aromatic parts of an aliphatic/aromatic copolymer was used in place of the styrene/hydrogenated terpene copolymer resin.

[0035]

EXAMPLE 6

In 700 parts of toluene were dissolved 100 parts of polyisobutylene having a weight average molecular weight of 550,000, 0.2 parts of an alkylphenolic resin, 0.1 part of poly[{6-(1,1,3,3-tetramethylbutyl)amino-1,3,5-triazine} {(2,2,6,6-tetramethyl-4-piperidyl)imino} hexamethylene {(2,2,6,6-tetramethyl-4-piperidyl)imino}], 0.2 parts of

an acrylic ester copolymer (Modaflow), and 1 part of a styrene/hydrogenated terpene copolymer resin (Clearon K100). A sheet for protecting a paint film was obtained in the same manner as in Example 1, except that the solution thus prepared was used.

[0036]

EXAMPLE 7

A sheet for protecting a paint film was obtained in the same manner as in Example 6, except that the amount of the styrene/hydrogenated terpene copolymer resin was changed to 5 parts.

[0037]

COMPARATIVE EXAMPLE 1

A sheet for protecting a paint film was obtained in the same manner as in Example 1, except that the styrene/hydrogenated terpene copolymer resin was omitted.

[0038]

COMPARATIVE EXAMPLE 2

A sheet for protecting a paint film was obtained in the same manner as in Example 6, except that the styrene/hydrogenated terpene copolymer resin was omitted.

[0039]

COMPARATIVE EXAMPLE 3

A sheet for protecting a paint film was obtained in the same manner as in Example 1, except that 1 part of a hydrogenated terpene resin (Clearon P-115, manufactured by Yasuhara Chemical Co., Ltd.) was incorporated in place of the styrene/hydrogenated terpene copolymer resin.

[0040]

EVALUATION TEST

The paint-protective sheets (50 mm square) obtained in the Examples and Comparative Examples were applied at 23°C to a paint film formed from Amilac 1000 (trade name; manufactured by Kansai Paint Co., Ltd.). The protective sheets applied

were subjected to a load test at 80°C for 24 hours or at 60°C and 95% RH for 24 hours, subsequently allowed to stand at 23°C for 1 hour, and then peeled off. After the peeling, the paint film was visually examined for fouling.

[0041]

The results of the evaluation are shown in the following Table.

	80°C, 24 hr	60°C/95%, 24 hr
Example 1	No fouling	No fouling
Example 2	No fouling	No fouling
Example 3	No fouling	No fouling
Example 4	No fouling	No fouling
Example 5	No fouling	No fouling
Example 6	No fouling	No fouling
Example 7	No fouling	No fouling
Comparative Example 1	Fouling occurred	Fouling occurred
Comparative Example 2	Fouling occurred	Fouling occurred
Comparative Example 3	Fouling occurred	Fouling occurred

Applicant: Nitto Denko Corporation

Applicant: Kansai Paint Co., Ltd.

Agent : Tsutomu Fujimoto

[Designation of Document] Abstract

[Abstract]

[Problem]

Development of a sheet for protecting a paint film which can be well adhered efficiently to a paint which is liable to retain fouling, sustains the adhered state over a long period of time, can easily be peeled off after accomplishment of the protection, is difficult to cause fouling of a paint film, and does not require a cleaning treatment.

[Means for Resolution]

A sheet for protecting a paint film comprising a substrate and formed thereon a rubber-based pressure-sensitive adhesive layer which comprises a rubbery polymer and incorporated therein at least a copolymer of an aromatic compound with a terpene compound or an aliphatic hydrocarbon compound.

[Selected Drawing] None